

AMENDMENTS TO THE CLAIMS:

Please amend Claims 55, 102, and 107. This listing of claims will replace all prior versions and listings of claims in the application:

Claims 1-54 (Canceled).

55. (Currently Amended) A process for producing tyres for vehicle wheels, the process comprising the steps of:

making a raw tyre comprising at least one crosslinkable elastomeric material;
molding the raw tyre in a molding cavity defined in a vulcanization mold; and
crosslinking the elastomeric material by heating the tyre to a predetermined

temperature for a predetermined time;

wherein the raw tyre comprises at least one crosslinkable elastomeric material comprising an elastomeric polymer containing epoxide groups and an active filler containing hydroxyl groups dispersed in the elastomeric polymer, said at least one crosslinkable elastomeric material has an effective degree of crosslinking equal to at least 65% after no more than 5 minutes of heating at 170°C, and wherein the crosslinking step is carried out essentially without additional crosslinking agents.

56. (Previously Presented) The process of claim 55, wherein the crosslinking step is carried out by heating the tyre to a maximum temperature of at least 100°C for at least 3 minutes.

57. (Previously Presented) The process of claim 56, wherein the crosslinking step is carried out by heating the tyre to a maximum temperature of at least 120°C for at least 5 minutes.

FINNEGAN
HENDERSON
FARABOW
GARRETT &
DUNNER LLP

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com

58. (Previously Presented) The process of claim 55, wherein the active filler is dispersed in the elastomeric polymer containing epoxide groups with a dispersion index greater than 90%.

59. (Previously Presented) The process of claim 58, wherein the active filler is dispersed in the elastomeric polymer containing epoxide groups with a dispersion index greater than 95%.

60. (Previously Presented) The process of claim 59, wherein the active filler is dispersed in the elastomeric polymer containing epoxide groups with a dispersion index greater than 98%

Claim 61. (Canceled).

62. (Previously Presented) A composition comprising an elastomeric polymer containing epoxide groups and an active filler containing hydroxyl groups dispersed in the elastomeric polymer, the composition being crosslinkable essentially without additional crosslinking agents and having an effective degree of crosslinking equal to at least 65% after no more than 5 minutes of heating at 170°C.

63. (Previously Presented) The composition of claim 62, wherein the active filler is dispersed in the elastomeric polymer containing epoxide groups with a dispersion index greater than 90%.

64. (Previously Presented) The composition of claim 63, wherein the active filler is dispersed in the elastomeric polymer containing epoxide groups with a dispersion index greater than 95%.

65. (Previously Presented) The composition of claim 64, wherein the active filler is dispersed in the elastomeric polymer containing epoxide groups with a dispersion index greater than 98%.

66. (Previously Presented) The composition of claim 62, wherein the elastomeric polymer containing epoxide groups is a homopolymer or copolymer with elastomeric properties having a glass transition temperature less than 23°C.

67. (Previously Presented) The composition of claim 66, wherein the elastomeric polymer containing epoxide groups has a glass transition temperature less than 0°C.

68. (Previously Presented) The composition of claim 62, wherein the elastomeric polymer contains at least 0.05 mol% of epoxide groups relative to a total number of moles of monomers present in the elastomeric polymer.

69. (Previously Presented) The composition of claim 68, wherein the elastomeric polymer contains from 0.1 mol% to 70 mol% of epoxide groups relative to the total number of moles of monomers present in the elastomeric polymer.

70. (Previously Presented) The composition of claim 69, wherein the elastomeric polymer contains from 0.5 mol% to 60 mol% of epoxide groups relative to the total number of moles of monomers present in the elastomeric polymer.

71. (Previously Presented) The composition of claim 62, wherein the elastomeric polymer has a mean molecular weight between 2,000 and 1,000,000.

72. (Previously Presented) The composition of claim 71, wherein the elastomeric polymer has a mean molecular weight between 50,000 and 500,000.

73. (Previously Presented) The composition of claim 62, wherein the elastomeric polymer is an epoxidized diene homopolymer or copolymer, in which a base polymer structure is derived from one or more conjugated diene monomers, optionally copolymerized with monovinylarenes, polar comonomers, or monovinylarenes and polar comonomers.

74. (Previously Presented) The composition of claim 73, wherein the base polymer structure is derived from natural rubber, polybutadiene, polyisoprene, styrene/butadiene copolymers, butadiene/isoprene copolymers, styrene/isoprene copolymers, nitrile rubbers, or mixtures thereof.

75. (Previously Presented) The composition of claim 62, wherein the elastomeric polymer is a copolymer of one or more monoolefins with an olefinic comonomer containing one or more epoxide groups.

76. (Previously Presented) The composition of claim 62, wherein the elastomeric polymer is a mixture with one or more non-epoxidized elastomeric polymers.

77. (Previously Presented) The composition of claim 62, wherein the active filler is silica, precipitated silica, pyrogenic silica, alumina, titanium oxide, cellulose fibres, microcrystalline cellulose, zeolites, kaolin, or mixtures thereof.

78. (Previously Presented) The composition of claim 77, wherein the active filler is precipitated silica, pyrogenic silica, alumina, or mixtures thereof.

79. (Previously Presented) The composition of claim 62, wherein the active filler is a filler whose surface is modified with hydroxyl groups.

80. (Previously Presented) The composition of claim 79, wherein the active filler is carbon black at least partially coated with silica.

81. (Previously Presented) The composition of claim 62, wherein a surface area of the active filler is greater than $40 \text{ m}^2/\text{g}$.

82. (Previously Presented) The composition of claim 81, wherein the surface area of the active filler is between $80 \text{ m}^2/\text{g}$ and $600 \text{ m}^2/\text{g}$.

83. (Previously Presented) The composition of claim 62, wherein the active filler has a density of active hydroxyl groups greater than $1 \text{ group}/\text{nm}^2$.

84. (Previously Presented) The composition of claim 83, wherein the active filler has a density of active hydroxyl groups greater than $5 \text{ groups}/\text{nm}^2$.

85. (Previously Presented) The composition of claim 62, wherein the active filler is present in an amount greater than 20 phr.

86. (Previously Presented) The composition of claim 85, wherein the active filler is present in an amount between 30 phr and 150 phr.

87. (Previously Presented) The composition of claim 62, wherein the active filler is mixed with one or more non-active reinforcing fillers.

88. (Previously Presented) The composition of claim 87, wherein the active filler is at least 50%-by-weight of total filler present in the composition.

89. (Previously Presented) The composition of claim 62, further comprising one or more of the following additives: antioxidants, protective agents, plasticizers, adhesives, anti-ozonizing agents, curing resins, modifying resins, and fibres.

90. (Previously Presented) The composition of claim 62, further comprising a lubricant.

91. (Previously Presented) The composition of claim 90, wherein the lubricant is present in an amount between 2 phr and 100 phr.

92. (Previously Presented) The composition of claim 91, wherein the lubricant is present in an amount between 5 phr and 50 phr.

93. (Previously Presented) A process for preparing an elastomeric composition comprising an elastomeric polymer containing epoxide groups and an active filler containing hydroxyl groups dispersed in the elastomeric polymer, the elastomeric composition being crosslinkable without additional crosslinking agents, the process comprising the step of mixing the active filler with the elastomeric polymer for a predetermined time, to obtain a degree of dispersion of the active filler greater than 90%, and at a predetermined temperature, to avoid pre-crosslinking of the elastomeric composition.

94. (Previously Presented) The process of claim 93, wherein a temperature of the mixing step is kept below 130°C.

95. (Previously Presented) The process of claim 94, wherein the temperature of the mixing step is kept below 100°C.

96. (Previously Presented) The process of claim 95, wherein the temperature of the mixing step is kept below 80°C.

97. (Previously Presented) The process of claim 93, wherein the active filler and the elastomeric polymer are mixed using an open mixer.

98. (Previously Presented) The process of claim 93, wherein the active filler and the elastomeric polymer are mixed using an internal mixer.

99. (Previously Presented) The process of claim 93, wherein the active filler and the elastomeric polymer are mixed using a continuous mixer.

100. (Previously Presented) The process of claim 97, 98, or 99, wherein a time of the mixing step is greater than 90 sec.

101. (Previously Presented) The process of claim 100, wherein the time of the mixing step is between 3 minutes and 35 minutes.

102. (Currently Amended) A process for preparing an elastomeric composition comprising an elastomeric polymer containing epoxide groups and an active filler containing hydroxyl groups dispersed in the elastomeric polymer, the elastomeric composition being crosslinkable without additional crosslinking agents, and wherein said active filler is dispersed in the elastomeric polymer containing epoxide groups with a dispersion index greater than 90%, the process comprising the steps of mixing the active filler with the elastomeric polymer in the form of an aqueous emulsion or a solution in an organic solvent, and then separating out by precipitation a mixture of the active filler and the elastomeric polymer.

103. (Previously Presented) A crosslinked manufactured product comprising an elastomeric polymer containing epoxide groups and an active filler containing hydroxyl groups dispersed in the elastomeric polymer, wherein the manufactured product is crosslinked essentially without additional crosslinking agents, and wherein the active filler is dispersed in the elastomeric polymer with a dispersion index greater than 90%.

104. (Previously Presented) The product of claim 103, wherein the active filler is dispersed in the elastomeric polymer containing epoxide groups with a dispersion index greater than 95%.

105. (Previously Presented) The product of claim 104, wherein the active filler is dispersed in the elastomeric polymer containing epoxide groups with a dispersion index greater than 98%.

106. (Previously Presented) The product of claim 103, obtained by crosslinking, essentially without additional crosslinking agents, a composition comprising an elastomeric polymer containing epoxide groups and an active filler containing hydroxyl groups dispersed in the elastomeric polymer, the composition having an effective degree of crosslinking equal to at least 65% after no more than 5 minutes of heating at 170°C.

107. (Currently Amended) A tyre for vehicle wheels, comprising one or more components made of crosslinked elastomeric material, wherein at least one of the components comprises a crosslinked elastomeric material comprising an elastomeric polymer containing epoxide groups and an active filler containing hydroxyl groups dispersed in the elastomeric polymer, the elastomeric material being crosslinked essentially without additional crosslinking agents, and wherein the crosslinkable elastomeric material has an effective degree of crosslinking equal to at least 65% after no more than 5 minutes of heating at 170°C.

Claim 108. (Canceled).